

WHAT IS CLAIMED IS:

1. A molding composition comprising the components  
of:

5 (A) a fibrous material;

(B) an inorganic filler;

at least one of (C) a radical polymerizable unsaturated  
polyester having an acid value of 3 to 60 KOHmg/g and (D)  
a radical polymerizable unsaturated polyester-polyamide having  
10 an acid value of 3 to 60 KOHmg/g; and

(E) a radical generator,

wherein the component (B) has been internally added  
to at least one of the components (C) and (D).

15 2. A molding composition comprising the components  
of:

(A) a fibrous material;

at least one of (C) a radical polymerizable unsaturated  
polyester having an acid value of 3 to 60 KOHmg/g and (D)  
20 a radical polymerizable unsaturated polyester-polyamide having  
an acid value of 3 to 60 KOHmg/g;

(E) a radical generator; and

(F) a di- or higher valent metal salt of a fatty acid.

25

3. The molding composition according to claim 1,  
wherein the component (B) has an average particle size of  
0.1 to 50  $\mu\text{m}$ .

5           4. The molding composition according to claim 1, which  
comprises 29 to 99% by weight of the component (A), 0.5 to  
70% by weight, in total, of the components (C) and (D), 0.1  
to 30% by weight of the component (E), each based on the total  
composition, and 0.1 to 70 parts by weight of the component  
10 (B) per 100 parts by weight of the total of the components  
(C) and (D).

5. The molding composition according to claim 2, which  
comprises 29 to 99% by weight of the component (A), 0.5 to  
15 70% by weight, in total, of the components (C) and (D), 0.1  
to 30% by weight of the component (E), and 0.1 to 10% by weight  
of the component (F) each based on the total composition.

6. The molding composition according to claim 2, which  
20 further comprises the component of (B) an inorganic filler.

7. The molding composition according to claim 6,  
wherein the component (B) is present in an amount of 0.1 to  
200 parts by weight per 100 parts by weight of the total of  
25 the components (C) and (D).

8. The molding composition according to claim 6,  
wherein the component (B) has an average particle size of  
0.1 to 50  $\mu\text{m}$ .

5

9. The molding composition according to claim 2,  
wherein the component (A) is organic fiber.

10. A molded article obtained by molding the molding  
composition according to claim 1.

11. A molded article obtained by molding the molding  
composition according to claim 2.

12. A resin composition comprising the components  
of at least one of (C) an unsaturated polyester having an  
acid value of 3 to 60 KOHmg/g and (D) an unsaturated  
polyester-polyamide having an acid value of 3 to 60 KOHmg/g  
and (B) an inorganic filler, wherein the component (B) has  
been internally added to at least one of the component (C)  
and (D).